

MACsoft 900

Technical Data Sheet

PRODUCT DESCRIPTION

MACsoft 900 is a range of super soft stabilized PVC films. Formulated for indoor and outdoor marking applications.

CONSTRUCTION

Face material :

Stabilized vinyl, 70 µm thick, cadmium-free.

Adhesive :

Permanent acrylic solvent based adhesive with low tack characteristics.

Liner :

Highly stable 135 gsm white kraft paper with blue backprinting.

TYPICAL USES

Specifically designed for plasticized banner markings (PVC coated textile) for sport or cultural events, exhibitions, street banners, short-term promotions (supermarkets, DIY stores, public houses), etc....

NB: Weak adhesion on polyester fabrics, polyolefine banners and non woven.

EXPECTED DURABILITY

The expected vertical outdoor durability of the unprocessed product in central Europe (Zone 1) is up to: 3 years.

This information is based on successful real life experience and artificial aging according to ISO4892-3.

Note : Exposure to severe temperatures and ultraviolet light, as well as conditions in southern European countries, and also in tropical, sub-tropical or desert regions, will cause a more rapid deterioration. This also applies to polluted areas, high altitude, horizontal and south-facing exposure.

SHELF LIFE

2 years when stored at 15 to 25°C and ± 50 % relative humidity.

PHYSICAL PROPERTIES (Typical values)

Thickness (mm) (Film + adhesive) ISO 534
0.110

Face Material Data, 23°C DIN 53455-5

Tensile strength : > 20 N/15mm

Elongation at break : ≥ 150 %

Adhesive Data, 23°C FTM 1

Peel adhesion 180° on stainless steel (N/25 mm)

- 20 min. residence: 14

- 24 hours residence: 16

- 1 week residence: 20

Dimensional stability

FTM 14

Shrinkage (48 hours at 70°C): < 0.5 %
(25 cm x 25 cm, sample mounted on aluminium).

Temperature ranges :

Application : + 10°C to + 40°C

End-use : - 20°C to + 70°C

N.B. : for lower temperatures, please consult us.

Flammability

ISO 3795

Sample mounted on aluminium: self-extinguishing.

CONVERTING

Screen printing

The printability of MACsoft 900 although possible, is not guaranteed.

Carefully check ink compatibility before proceeding with a production run.

Computer cutting

Clean, quick, trouble-free cutting with most plotters. Easy and fast weeding even down to small letters and fine lines. Adjustment of the cutting depth is important : if the cut is too deep this could result in the paper splitting and coming away with the adhesive when the vinyl is transferred to Application Tape.

Application

The use of lacquered banner material is recommended in order to avoid or reduce possible plasticizer migration into the MACsoft 900 adhesive. In any case the compatibility of MACsoft 900 with the banner material must be tested before a production run.

The cleaning of the banner material with alcohol is recommended to remove possible migratory agents from the banner surface.

MACtransfer Application Tape aids the application of MACsoft 900 onto the banners.

MACsoft 900 used with a plasticized banner has a low initial adhesion. This allows a repositioning of the decal. We recommend to wait a few minutes before removing the Application Tape.

Cleaning

Use slightly soapy water.

Removal of letters and recovery of banner

When removing letters, some adhesive residue may remain on the banner. To clean the banner, we recommend the use of denatured ethanol or isopropyl alcohol.

IMPORTANT NOTICE

All MACTac products are subject to careful quality control throughout the manufacturing process and are warranted to be of merchantable quality and free from manufacturing defects. Published information concerning MACTac products is based upon research which the Company believes to be reliable although such information does not constitute a warranty. Because of the variety of uses of MACTac products and the continuing development of new applications, the purchaser should carefully consider the suitability and performance of the product for each intended use, and the purchaser shall assume all risks regarding such use. The seller shall not be liable for damages in excess of the purchase price of the product nor for incidental or consequential damages. All specifications are subject to change without prior notice.